

USSN: 09/698735

Docket No.: 53494US017


REMARKS

Upon review of the allowed claims, it was noted that each of claims 38, 41, 43 and 46 recited "track time" rather than "track-free time". Correction of this inadvertent error is respectfully requested.

Registration Number 39,091	Telephone Number 651/575-3915
Date 5-7-02	

Respectfully submitted,

By


Carolyn A. Fischer

Office of Intellectual Property Counsel
3M Innovative Properties Company
P.O. Box 33427
St. Paul, Minnesota 55133-3427
Facsimile: (651) 736-3833

USPN: 09/698735

Doctet No.: 53494U8017

Version With Markings to Show Changes Made**38. A pavement marking comprising:**

a binder having polyurea groups, wherein the binder is prepared from a coating composition comprising:

- one or more aliphatic secondary amines;
- one or more polyisocyanates;
- material selected from the group consisting of fillers, extenders, pigments, and combinations thereof; and
- reflective elements;

wherein the coating composition has a track-free time of no greater than about 5 minutes.

41. A pavement marking comprising:

a binder having polyurea groups, wherein the binder is prepared from a coating composition comprising:

- one or more aliphatic secondary amines;
- one or more polyisocyanates;
- material selected from the group consisting of fillers, extenders, pigments, and combinations thereof; and
- reflective elements;

wherein the coating has an open time of at least 30 seconds and a track-free time of no greater than about 5 minutes.

43. A pavement marking comprising:

a binder having polyurea groups, wherein the binder is prepared from a coating composition comprising:

- one or more aliphatic secondary amines;
- one or more polyisocyanates;
- material selected from the group consisting of fillers, extenders, pigments, and combinations thereof; and
- reflective elements;

USPN: 09/698735

Docket No.: 53494UB017

wherein the coating has a track-free time of no greater than about 5 minutes and a retained reflectivity of at least 100 mod/m²/lux after at least 2 years in use as longitudinal traffic markings as measured according to ASTM E 1710-95.

46. A pavement marking comprising:

a binder having polyurea groups, wherein the binder is prepared from a coating composition comprising

one or more aliphatic secondary amines comprising an aspartic ester amine;

one or more polyisocyanates;

material selected from the group consisting of fillers, extenders, pigments, and combinations thereof; and

reflective elements;

wherein the coating has a track-free time of no greater than about 5 minutes.